

## Type

Solvent-free colourfast 1-component binder on a polyurethane basis.

## Applications

Strizo PU 250 is used as a binder for Strizo gravel and Marmorstone carpets in outdoor applications.

## Packaging

Units of 1.6 kg each.

## Technical specifications

Colour	: transparent
Density	: 1.00 Kg/l
Compression strength	: > 40 N/mm <sup>2</sup>
Bending tensile strength	: > 50 N/mm <sup>2</sup>
Processing time	: 25 minutes at 20°C
Curing time	: 24 hours at 20°C
Recommended quantity	: 4% for 2–3 mm gravel
Handling temperature	: min. +10°C – max. +30°C
Shelf life temperature	: 12 months at room temperature



## Application instructions

To be applied in accordance with the instructions for Comosil floor systems. First mix Strizo PU 250 mechanically, then add it gradually to the gravel mix. Use a low-speed mechanical mixing tool to minimise air intake.

## Composition

- Strizo EP 110
- Strizo PU 250 + gravel

Do not seal outdoor applications.

## Properties

- Solvent-free
- Colourfast
- Non-inflammable
- Easy to process

The data above has been gathered from the existing literature with the utmost care. Comosil B.V. does not accept any liability for damage of whatever nature or size arising from the use of this data.

1 September 2005