

Type

Solvent-free 2-component cast floor based on special polyurethane resins.

Applications

Strizo PU 60/80 MP is a technical solution for stable substrates in areas where permanent system flexibility is required. Strizo PU 60/80 MP is available in two hardness grades. Grade 80 offers high-performance mechanical properties; grade 60 is particularly suitable in areas where user comfort is an important consideration. Note that the material is not colourfast, and that the use of a floor sealant is recommended.

Packaging

Units of 30 kg each.

Technical specifications

Colour	: high-gloss, colour category 1 (other colours available on request)
Density	: 1.5 kg/l
Compression strength	: >40 / >60 N/mm ²
Shore D	: approx. 50° / 80°
Processing time	: 30 min. at 20°C
Curing time	: can be walked on after 16 hrs.; full chemical curing after 2 days at 20°C
Recommended thickness	: 2–3 mm
Handling temperature	: min. +13°C – max. +30°C
Shelf life temperature	: 12 months at room temperature



Application instructions

To be applied in accordance with Comosil application instructions for Strizo PU 60/80 MP floors.

Composition

- Strizo EP 110
- Strizo PU 60/80 MP
- Strizo PU 380

Properties

- Solvent-free
- Non-inflammable
- Highly resistant to chemicals
- Wear-resistant
- Allows fluid-tight applications according to the CUR 44 guideline and/or HACCP standards
- Seamless and aesthetic

Safety

See Strizo PU 60/80 MP Safety Info Sheet

The data above has been gathered from the existing literature with the utmost care.
Comosil B.V. does not accept any liability for damage of whatever nature or size arising from the use of this data.

1 September 2005